

CERAKOTE®

ASTM D2794: IMPACT RESISTANCE

Impact Resistance (ASTM D2794) measures the resistance of organic coatings to the effects of rapid deformation (Impact). Impact resistance is measured by placing a coated panel in an universal impact tester. A standard weight is dropped a distance to strike an indenter that deforms the coating and the substrate. The indentation can be either an intrusion or an extrusion. By gradually increasing the distance the weight drops, (2 inches at a time) the point at which failure occurs can be determined by cracking or delamination of the coating. All Cerakote® Elite and nearly every Cerakote® H Series have an impact strength measuring 160 in-lbs., which is the maximum the impact tester can measure.



INNOVATIONS OF NIC INDUSTRIES

PRISMATIC POWDERS | CERAKOTE | CERAKOTE TRIM

WWW.CERAKOTE.COM 866-774-7628



7050 6TH STREET WHITE CITY, OR 97503